

Polybutylene Terephthalate (PBT)

DURANEX®

2000

EF2001/PLT9908

HB, standard

Introduction

Noted for its excellent properties and superior injection molding characteristics,

DURANEX[®] PBT resin has been widely used in a variety of industries such as electrical/electronics and automotive manufacturing.

Various **DURANEX** grades are available to meet specific requirements in a wide range of applications.

The general-purpose (slow burning) glassfiber reinforced grades offer high strength, high rigidity, and superior heat

resistance (available with glass fiber contents of 15%, 20%, 30%, 40%, and 45%).

However, these grades are sometimes prone to problems such as distortion, deformation, and anisotropic physical properties due to the orientation of the glass fiber.

Consequently, for applications where flexibility is more important than rigidity, the general-purpose (slow burning) unfilled grades, **DURANEX 2000** and **2002** are more suitable.

DURANEX 2000 has superior flow characteristics during injection molding.

General Properties of 2000

table1-1 General Properties (ISO)

Item	Unit	Test Method	HB, standard
			2000
			Unfilled, high flow
Color			EF2001/PLT9908
ISO(JIS)quality-of-the-material display:		ISO11469 (JIS K6999)	>PBT<
Density	g/cm ³	ISO 1183	1.31
Water absorption (23°C,24hrs,1mmt)	%	ISO 62	0.2
Tensile strength	MPa	ISO 527-1,2	60
Strain at break	%	ISO 527-1,2	20 ^{*1}
Flexural strength	MPa	ISO 178	89
Flexural modulus	MPa	ISO 178	2,500
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	3.2
Temperature of deflection under load (1.8MPa)	°C	ISO 75-1,2	73
Coefficient of linear thermal expansion (23 - 55°C、 Flow direction)	x10 ⁻⁵ /°C	Our standard	11
Coefficient of linear thermal expansion (23 - 55°C、 Transverse direction)	x10 ⁻⁵ /°C	Our standard	11
Electric strength (3mmt)	kV/mm	IEC 60243-1	17
Volume resistivity	Ω·cm	IEC 60093	5 × 10 ¹⁶
Tracking resistance (CTI)	V	IEC 60112	-
Rockwell hardness	M(Scale)	ISO2039-2	90
Flammability		UL94	HB
The yellow card File No.			E213445
Appropriate List number of Ministerial Ordinance for Export Trade Control			Item 16 of Appendix -1

*1) Nominal strain at break

All figures in the table are the typical values of the material and not the minimum values of the material specifications.


2. Processing characteristics of DURANEX® 2000

2.1 Flow characteristics

In Figure 2-1, the bar flow lengths of 2000 are compared with that of the standard glass-fiber reinforced grade 3300. Compared to 3300, the bar

flow length of 2000 is much longer. The grade most suitable for the shape of the molding and type of application should be selected.

Figure 2-1 Bar Flow Length of DURANEX® 2000



Processing parameters (Nozzle)
Cylinder temperature : 250-240-220-200°C
Mold temperature : 75°C
Injection speed : 50mm/s
Cycle time : 12s hold phase/8s cooling
Mold : Bar flow test mold
Cavity depth : 2mm


2.2 Molding shrinkage

shrinkage does not show any anisotropic behavior.

Figure 2-2 shows the molding shrinkage of 2000.

Unlike the glass-fiber reinforced grades, its molding

Figure 2-2 Molding shrinkage of DURANEX® 2000 (Flow Direction)



Processing parameters ^(Nozzle)
 Cylinder temperature : 240-240-220-220 °C
 Mold temperature : 65 °C
 Injection speed : 33mm/s
 Cycle time : Thickness 2f 3f 4f
 Hold phase 10s 20s 30s
 Cooling 10s 10s 10s
 Mold : 20×120mm×2, 3, and 4mm t flat plate
 Gate size : 4 (w) × 2 (t)

NOTES TO USERS

- All property values shown in this brochure are the typical values obtained under conditions prescribed by applicable standards and test methods.
- This brochure has been prepared based on our own experiences and laboratory test data, and therefore all data shown here are not always applicable to parts used under different conditions. We do not guarantee that these data are directly applicable to the application conditions of users and we ask each user to make his own decision on the application.
- It is the users' responsibility to investigate patent rights, service life and potentiality of applications introduced in this brochure. Materials we supply are not intended for the implant applications in the medical and dental fields, and therefore are not recommended for such uses.
- For all works done properly, it is advised to refer to appropriate technical catalogs for specific material processing.
- For safe handling of materials we supply, it is advised to refer to the Safety Data Sheet "SDS" of the proper material.
- This brochure is edited based on reference literature, information and data available to us at the time of creation. The contents of this brochure are subject to change without notice upon achievement of new data.
- Please contact our office for any questions about products we supply, descriptive literatures or any description in this brochure.

DURANEX® is a registered trademark of Polyplastics Co., Ltd. in Japan and other countries.

POLYPLASTICS CO., LTD.

JR Shinagawa East Bldg.,
18-1, Konan 2-chome, Minato-ku, Tokyo, 108-8280 Japan
Tel: +81-3-6711-8610 Fax: +81-3-6711-8618

<http://www.polyplastics.com/en/>