

ENGITECH® C00 100000

Technical Data Sheet

Compound in PBT

PRODUCT DESCRIPTION

ENGITECH® C00 100000 is a non-reinforced PBT with balanced mechanical properties and good flowability

Property	Test Condition	Unit	Standard	Typical value
Mechanical properties (23 °C/50 % r. h.)				
Tensile strength	50 mm/min	MPa	ASTM D638	45
Tensile elongation	50 mm/min	%	ASTM D638	>50
Izod impact strength (notched)	23 °C	J/m	ASTM D256	55
Thermal properties				
Melting temperature	10 °C/min	°C	ASTM D3418	225
Other properties (23 °C)				
Density		g/cc	ASTM D792	1.31
Intrinsic Viscosity		dl/g	PBI	1.1
MFI	250°C / 2.16 kg	gm/10 min	ASTM D 1238	14-20
Processing recommendations				
Drying temperature dry air dryer		°C		120
Drying time dry air dryer		h		3-4
Residual moisture content		%	Karl Fischer	0.1 (max)

USAGE

ENGITECH® C00 100000 is especially suited for injection molding of general purpose application

STORAGE AND SHELF LIFE

It is recommended to store ENGITECH® C00 100000 compound in dry, dust free sealed conditions and prevent exposure to direct sunlight and/or heat. The storage should not exceed 12 months at 25°C for optimum performance. Higher temperature might reduce storage time considerably.

Version 29072020

*The information and recommendations contained herein are believed to be accurate and should only be used as a guide. With respect to this publication and the product related thereto, manufacturer makes no guarantee or warranty of any kind, express or implied and shall not be liable for consequential or incidental losses or damages resulting from use of this publication or handling or use of product, including, health related damages or injuries or infringement of intellectual property rights. The person receiving it shall make his own determination, through proper trials and evaluation about the suitability of the information or product for his particular use.