



ISONYL	Code	
	Grade	A 6 GF30 V0
	Polymer	PA 6
	Application	Injection Moulding

30% glass fiber. Flame retardant grade with halogens.

Properties	Method	Unit	Value
Physical			
Density at 23°C	ISO 1183	g/cm3	1,60-1,62
Mould Shrinkage [§] (%)	INTERNAL	%	0,2-0,4
Thermal			
VICAT B50	ISO 306	°C	200
HDT, A (1,80 MPa)	ISO 75/Af	°C	195
HDT, A (0,45 MPa)	ISO 75/Af	°C	215
Mechanical at 23 ºC			
Flexural Modulus (23°C - 2 mm/min)	ISO 178	MPa	9000
Flexural strength (23°C - 2 mm/min)	ISO 178	MPa	200
Tensile Modulus (23°C - 1 mm/min)	ISO 527	MPa	10000
Tensile strength at break (23°C - 5 mm/min)	ISO 527	MPa	120
Tensile elong. at break (23°C - 5 mm/min)	ISO 527	%	5,0
Izod notched impact strength (23°C) ISO	ISO 180/1A	KJ/m²	10
Charpy unnotched impact strength (23°C)	ISO 179/1eU	KJ/m²	50
Flammability			
Glow Wire Flammability Index GWFI (1,0 mm)	IEC 606925-2-12	°C	960
Glow Wire Flammability Index GWFI (3,0 mm)	IEC 606925-2-12	°C	960
Flammability class (0,8 mm)	UL 94		V0
Flammability class (3,0 mm)	UL 94		V0



Processing Conditions			
Melt Temperature Range	ISO 294	°C	240-270
Mold Temperature Range	ISO 294	°C	70-90
Injection Velocity	ISO 294		MEDIUM
Drying Temperature		°C	80-100
Drying Time		Hour	3

Regulations compliance	
RoHS compliance status:	COMPLIANT
EN71:	
UL listed file nº:	
Water contact approvals.	
Food contact status:	

Technical documents	
Material safety datasheet:	http://www.sirmax.it/sites/default/files/ISONYL%C2%AE%20MSDS.pdf

Revision number/date: 0 MAR 21

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

The value above is the representative value of the NP standard and may have deviation. It can only be used for selecting materials and shall not be regarded as a material specification and cannot be used for molding designs.

[§] Moulding shrinkage is not an intrinsic property of plastics. It also depends on moulding parameters. The values reported have been calculated in the direction parallel to the flow in a 3.0 x 12.7 x 127 mm sample.

ISO Datasheet



Information inserted in this document such as data, statements, representative values, etc. are provided solely for customer convenience. It does not expressly or impliedly guarantee anything regarding the safety or practicability of the (1) materials, (2) products, and/or (3) design that utilizes recommendations or proposals, of Sirmax. Furthermore, nothing in the contents of this document shall have any legal binding effect, and especially, the representative value is simply for reference and is not a minimum value that has legal binding effect.

Whether materials and/or products of Sirmax and/or a design that uses or utilizes Sirmax recommendations or proposals are (is) compatible with individual uses shall be determined solely by each user and such user shall be solely responsible for any results, including but not limited to, any and all loss and damages incurred due to such uses. Users must implement and verify all testing and analyses for proving the safety and compatibility of final products that have been created or altered by using Sirmax's materials or products. The data and values inserted and/or contained in this document may be changed due to quality improvement of the product without any prior notification.