

LUPOY EF1006F

Injection Molding, PC, Cl/Br Free Flame Retardancy

Description

General Purpose
UL746C f1

Application

Electronics, Home Appliances, Industrial Goods

Properties	Condition	Method	Unit	Typical Value
Physical				
Specific Gravity	23°C	ASTM D792		1.21
Shrinkage		ASTM D955		
Flow	2.0mm		%	0.6~0.8
Cross-flow	2.0mm		%	0.7~0.9
Melt Flow Rate	300°C, 1.2kg	ASTM D1238	g/10min	10.1
Water Absorption	23°C, 50% RH	ASTM D570	%	0.20
Mechanical				
Tensile Strength		ASTM D638		
@Yield	3.2mm, 50mm/min		kgf/cm ²	630
@Break	3.2mm, 50mm/min		kgf/cm ²	720
Tensile Elongation		ASTM D638		
@Yield	3.2mm, 50mm/min		%	6
@Break	3.2mm, 50mm/min		%	120
Tensile Modulus	3.2mm, 50mm/min	ASTM D638	kgf/cm ²	23,100
Flexural Strength	3.2mm, 10mm/min	ASTM D790	kgf/cm ²	1,030
Flexural Modulus	3.2mm, 10mm/min	ASTM D790	kgf/cm ²	22,380
IZOD Impact Strength		ASTM D256		
3.2mm, Notched	23°C		kgf·cm/cm	84.6
	-30°C		kgf·cm/cm	10.0
6.4mm, Notched	23°C		kgf·cm/cm	12.0
	-30°C		kgf·cm/cm	10.0
	-40°C		kgf·cm/cm	9.0
Rockwell Hardness	R-Scale	ASTM D785		118
Thermal				
Heat Deflection Temperature		ASTM D648		
4.6kgf	6.4mm, Unannealed		°C	141
18.6kgf	6.4mm, Unannealed		°C	130
Vicat Softening Temperature	5kg, 50°C/hr	ASTM D1525	°C	140
Coefficient of Linear Thermal Expansion		ASTM D696		
Flow	-30°C ~ 80°C		10 ⁻⁶ m/m·°C	74
Cross-flow	-30°C ~ 80°C		10 ⁻⁶ m/m·°C	72

Note) Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow rate are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Issued Date : 2025-12-16

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

LUPOY EF1006F

Injection Molding, PC, Cl/Br Free Flame Retardancy

Description

General Purpose
UL746C f1

Application

Electronics, Home Appliances, Industrial Goods

Flammability

Flammability		UL94	mm, Class	2.5mm, 5VA
Relative Temperature Index(RTI)		UL746B		
Electrical	Min. Thickness		mm	1.00
	Temp		°C	125
	Max. Temp		°C	125
	Thickness		mm	1.00
Mechanical With Impact	Min. Thickness		mm	1.00
	Temp		°C	120
	Max. Temp		°C	120
	Thickness		mm	1.00
Mechanical Without Impact	Min. Thickness		mm	1.00
	Temp		°C	125
	Max. Temp		°C	125
	Thickness		mm	1.00

Electrical

Comparative Tracking Index(CTI)	Solution A	UL746A	PLC	3
Surface Resistivity	23°C	ASTM D257	Ohm	1E+15
Volume Resistivity	23°C	ASTM D257	Ohm·cm	1E+15
Dielectric Constant	23°C	ASTM D150		2.8
Dielectric Strength	23°C, 2.0mm	ASTM D149	kV/mm	20

Note) Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow rate are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Issued Date : 2025-12-16

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

LUPOY EF1006F

Injection Molding, PC, Cl/Br Free Flame Retardancy

Description

General Purpose
UL746C f1

Application

Electronics, Home Appliances, Industrial Goods

Processing Conditions (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	100 ~ 120
Drying Time	hrs	3~5
Maximum Moisture Content	%	0.02
Melt Temperature	°C	300 ~ 320
Cylinder Temperature	Rear	°C 260 ~ 280
	Middle	°C 280 ~ 300
	Front	°C 300 ~ 320
Nozzle Temperature	°C	300 ~ 320
Mold Temperature	°C	80 ~ 120

Note) These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

Note) Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow rate are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Issued Date : 2025-12-16

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.