## N1 020 GF BLK POLYAMIDE (PA-6)



### **PRODUCT DESCRIPTION**

Nylon 6 20% Glass Filled Black

### FEATURES

- Glass Filled
- Excellent Mechanical & Chemical properties

### **APPLICATIONS**

- Furniture
- Automotive
- Home appliance

|  | TECT   | UNIT | TYPICAL    |
|--|--------|------|------------|
| TYPICAL PROPERTIES                     | TEST   | UNIT |            |
|  | METHOD |      | VALUES     |
| PHYSICAL PROPERTIES                    |        |      |            |
|  | 5 700  | ,    | 4.97       |
| Density                                | D-792  | g/cc | 1.27       |
| Shrinkage                              | D-1299 | %    | 0.5 – 0.7% |
|  |        |      |            |
| MECHANICAL PROPERTIES                  |        |      |            |
|  |        |      |            |
| Tensile Strength Yield                 | D-638  | MPa  | 140        |
| Elongation Break                       | D-638  | %    | 3          |
| Flexural Strength,                     | D-790  | MPa  | 180        |
| Impact Strength (IZOD Notched)         | D-256  | J/m  | 7          |
|  |        | -    |            |
| THERMAL PROPERTIES                     |        |      |            |
|  |        |      |            |
| Heat Deflection Temperature Method P   | D-648  | °C   | 205        |
| Heat Deflection Temperature - Method B | D-040  | Ľ    | 205        |
|  |        |      |            |

# Ravago Manufacturing India Pvt Ltd.

96, GIDC Alindra, Manjusar, Tal. Savali, Vadodara 391775. India +919909901581 Format No: F-QC-20

# www.ravagomi.com Rev.No:01



| TYPICAL PROPERTIES | TEST<br>METHOD | UNIT | TYPICAL<br>VALUES |
|--------------------|----------------|------|-------------------|
| FLAMMABILITY       |                |      |                   |
|                    |                |      |                   |
| Flame Rating       | UL 94          | -    | НВ                |
| Glow Wire Testing  | IEC 60695-     | °C   | NA                |
|                    | 2-12           |      |                   |

| INJECTION MOLDING CONDITIONS |    |            |
|------------------------------|----|------------|
|                              |    |            |
| Mold Temperature             | °C | 80 to 100  |
| Rear Temperature             | °C | 220 to 230 |
| Middle Temperature           | °C | 230 to 240 |
| Front Temperature            | °C | 240 to 250 |
| Nozzle Temperature           | °C | 250 to 255 |

#### **Drying Conditions**

Material can be dried for 4 hours at 90 - 100°C or until moisture level <0.2%.

### HANDLING AND STORAGE

**Handling:** Maintain good housekeeping. Spilled materials may create a slipping hazard. Remove dust from settling areas to prevent any secondary potential dust explosion or fire hazards. Electrostatic charge may build up during handling. Grounding of equipment is recommended.

**Storage:** Store in a dry place and away from direct sunlight or heat sources.

### **DISPOSAL CONSIDERATIONS**

Disposal Method: It must be disposed of in accordance with Federal, State and local environmental control regulations.

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

### Ravago Manufacturing India Pvt Ltd.

Format No: F-QC-20

