

N2 030 GF NTR POLYAMIDE (PA-66)



PRODUCT DESCRIPTION

Nylon 66 30% Glass Filled Natural.

FEATURES

- Improved Mechanical & Chemical properties

APPLICATIONS

- Automotive
- Home appliance

TYPICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES
PHYSICAL PROPERTIES			
Density	D-792	g/cc	1.38
Shrinkage	D-1299	%	0.3
Melting Point	D-7138	°C	265
MECHANICAL PROPERTIES			
Tensile Strength Yield	D-638	MPa	155
Elongation Break	D-638	%	3.5
Flexural Strength,	D-790	MPa	255
Flexural Modulus	D-790	MPa	8000
Impact Strength (IZOD Notched)	D-256	J/m	12
THERMAL PROPERTIES			
Heat Deflection Temperature - Method B	D-648	°C	205
Vicat Softening Temperature @ 50N	D-1525	°C	NA

Ravago Manufacturing India Pvt Ltd.

96, GIDC Alindra, Manjusar,
Tal. Savali, Vadodara 391775. India

☎ +919909901581

Format No: F-QC-20

 www.ravagomi.com

Rev.No:01

N2 030 GF NTR POLYAMIDE (PA-66)



TYPICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES
FLAMMABILITY			
Flame Rating	UL 94	-	HB
Glow Wire Testing	IEC 60695-2-12		NA

INJECTION MOLDING CONDITIONS			
Mold Temperature		°C	80 to 100
Rear Temperature		°C	260 to 265
Middle Temperature		°C	265 to 270
Front Temperature		°C	270 to 280
Nozzle Temperature		°C	280 to 300

Drying Conditions

Material can be dried for 4 hours at 90 - 100°C or until moisture level <0.2%.

HANDLING AND STORAGE

Handling: Maintain good housekeeping. Spilled materials may create a slipping hazard. Remove dust from settling areas to prevent any secondary potential dust explosion or fire hazards. Electrostatic charge may build up during handling. Grounding of equipment is recommended.

Storage: Store in a dry place and away from direct sunlight or heat sources.

DISPOSAL CONSIDERATIONS

Disposal Method: It must be disposed of in accordance with Federal, State and local environmental control regulations.

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Manufacturing India Pvt Ltd.

96, GIDC Alindra, Manjusr,
Tal. Savali, Vadodara 391775. India

☎ +919909901581

Format No: F-QC-20

 www.ravagomi.com

Rev.No:01