

# PC 300 UF R WHITE POLYCARBONATES



## PRODUCT DESCRIPTION

PC Unfilled White

## FEATURES

- Improved Impact Strength
- Excellent Surface Finish
- Excellent Mechanical

## APPLICATIONS

- Electrical & Electronic

TYPICAL PROPERTIES	TEST ASTM	UNIT	Typical Values
<b>PHYSICAL PROPERTIES</b>			
Density	D-792	g/cc	1.20 ± 0.02
Ash Content / Reinforcement	D-5630	%	NA
Melt Flow Index	D-1238	g/10min	20 ± 5
Shrinkage	D-1299	%	0.5 - 0.8
<b>MECHANICAL PROPERTIES</b>			
Tensile Strength Yield	D-638	MPa	≥ 60
Elongation Break	D-638	%	≥ 35
Flexural Strength,	D-790	MPa	≥ 65
Flexural Modulus	D-790	MPa	≥ 1900
Impact Strength (IZOD Notched)	D-256	Kg cm/cm	≥ 60
<b>THERMAL PROPERTIES</b>			
Heat Deflection Temperature - Method B	D-648	°C	≥ 105
Vicat Softening Temperature @ 50N	D-1525	°C	≥ 120

## Ravago Manufacturing India Pvt Ltd.

96, GIDC Alindra, Manjusar,  
Tal. Savali, Vadodara 391775. India

☎ +919909901581  
Format No: F-QC-20

 [www.ravagomi.com](http://www.ravagomi.com)  
Rev.No:01

# PC 300 UF R WHITE POLYCARBONATES



TYPICAL PROPERTIES	TEST ASTM	UNIT	Test Values
<b>FLAMMABILITY</b>			
Flame Rating	UL 94	-	HB
Glow Wire Testing	EIC 60695-2-12		NA

<b>INJECTION MOLDING CONDITIONS</b>			
Mold Temperature		°C	80 to 90
Rear Temperature		°C	240 to 250
Middle Temperature		°C	250 to 260
Front Temperature		°C	260 to 270
Nozzle Temperature		°C	270 to 280

### **Drying Conditions**

It is not necessary to pre-dry this material but in the event of moisture accumulation or evidence of splay, the material can be dried for 2-3 hours at 90 - 100°C.

### **HANDLING AND STORAGE**

**Handling:** Maintain good housekeeping. Spilled materials may create a slipping hazard. Remove dust from settling areas to prevent any secondary potential dust explosion or fire hazards. Electrostatic charge may build up during handling. Grounding of equipment is recommended.

**Storage:** Store in a dry place and away from direct sunlight or heat sources.

**NOTE:** Possible presence of metallic particles < 0.8 mm.

### **DISPOSAL CONSIDERATIONS**

**Disposal Method:** It must be disposed of in accordance with Federal, State and local environmental control regulations.

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## **Ravago Manufacturing India Pvt Ltd.**

96, GIDC Alindra, Manjusar,  
Tal. Savali, Vadodara 391775. India

☎ +919909901581  
Format No: F-QC-20



[www.ravagomi.com](http://www.ravagomi.com)

Rev.No:01