

PP 000 UF P262 C

POLYPROPYLENE



PRODUCT DESCRIPTION

PP UNFILLED PURPULE

FEATURES

- Excellent Impact Strength
- Excellent Surface Finish
- Excellent Mechanical

APPLICATIONS

- Furniture
- Automotive
- Home appliance

TYPICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES
PHYSICAL PROPERTIES			
Density	D-792	g/cc	0.90
Mold Shrinkage	D-955	%	0.5
MECHANICAL PROPERTIES			
Tensile Strength Yield	D-638	MPa	31
Elongation Break	D-638	%	60
Flexural Strength,	D-790	MPa	31
Flexural Modulus	D-790	MPa	900
Impact Strength (IZOD Notched)	D-256	Kg cm/cm	6
THERMAL PROPERTIES			
Heat Deflection Temperature - Method B	D-648	°C	121

Ravago Manufacturing India Pvt Ltd.

96, GIDC Alindra, Manjusar,
Tal. Savali, Vadodara 391775. India

☎ +919909901581

Format No: F-QC-20

 www.ravagomi.com

Rev.No:01

TYPICAL PROPERTIES	TEST METHD	UNIT	TYPICAL VALUES
FLAMMABILITY			
Flame Rating	UL 94	-	HB
Glow Wire Testing	IEC 60695-2-12		NA

INJECTION MOLDING CONDITIONS			
Mold Temperature		°C	80 to 90
Rear Temperature		°C	190 to 210
Middle Temperature		°C	195 to 215
Front Temperature		°C	190 to 220
Nozzle Temperature		°C	190 to 220

Drying Conditions

It is not necessary to pre-dry this material but in the event of moisture accumulation or evidence of splay, the material can be dried for 2-3 hours at 90 - 100°C.

HANDLING AND STORAGE

Handling: Maintain good housekeeping. Spilled materials may create a slipping hazard. Remove dust from settling areas to prevent any secondary potential dust explosion or fire hazards. Electrostatic charge may build up during handling. Grounding of equipment is recommended.

Storage: Store in a dry place and away from direct sunlight or heat sources.

DISPOSAL CONSIDERATIONS

Disposal Method: It must be disposed of in accordance with Federal, State and local environmental control regulations.

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Manufacturing India Pvt Ltd.

96, GIDC Alindra, Manjusar,
Tal. Savali, Vadodara 391775. India

☎ +919909901581

Format No: F-QC-20

 www.ravagomi.com

Rev.No:01