

| | | |
|---------|------------|---------|
| storex® | Grade | VH-0815 |
| | Resin Type | ABS |

Flame Retardant, E&E, Home Appliances, Wiring Devices

| Item | Measuring Method | Condition | Unit | Value |
|-------------------------------|------------------|----------------------------------|---------|-----------|
| Physical | | | | |
| Specific Gravity | ASTM D792 | Natural or representative color | - | 1.15 |
| Melt Flow Index | ASTM D1238 | 200°C, 5kg | g/10min | 3.8 |
| Mold Shrinkage(MD) | ASTM D955 | Flow at 3.2mm(MD) | % | 0.34~0.41 |
| Mold Shrinkage(TD) | ASTM D955 | X-Flow at 3.2mm(TD) | % | 0.36~0.44 |
| Mechanical | | | | |
| Tensile Strength at Yield | ASTM D638 | 5mm/min | MPa | 39 |
| Tensile Strain at break | ASTM D638 | 5mm/min | % | 17 |
| Tensile Modulus | ASTM D638 | 5mm/min | MPa | 2000 |
| Tensile Strength at break | ASTM D638 | 5mm/min | MPa | 27 |
| Flexural Strength | ASTM D790 | 2.8mm/min | MPa | 59 |
| Flexural Modulus | ASTM D790 | 2.8mm/min | MPa | 2200 |
| Izod Impact Strength(notched) | ASTM D256 | 1/4 inch at 23°C | J/m | 250 |
| Rockwell Hardness | ASTM D785 | R-Scale | - | 100 |
| Thermal | | | | |
| Heat Deflection Temperature | ASTM D648 | 18.56kgf/cm ² , 6.4mm | °C | 77 |
| VICAT Softening Temperature | ISO 306 | B/50 | °C | 86 |
| Flammability | | | | |
| Flammability | UL94 | V-1 | mm | 1.5 |
| Flammability | UL94 | V-0 | mm | 2 |
| Flammability | UL94 | 5VB | mm | 2 |

1. The value above is the representative value of the NP or representative color and may have deviation. It can only be used for selecting materials.
2. The value above shall not be regarded as a material specification and cannot be used for molding designs.

Information inserted in this document such as data, statements, representative values, etc. are provided solely for customer convenience. It does not expressly or impliedly guarantee anything regarding the safety or practicability of the (1) materials, (2) products, and/or (3) design that utilizes recommendations or proposals, of LOTTE Advanced Materials. Furthermore, nothing in the contents of this document shall have any legal binding effect, and especially, the representative value is simply for reference and is not a minimum value that has legal binding effect.

Whether materials and/or products of LOTTE Advanced Materials and/or a design that uses or utilizes LOTTE Advanced Materials' recommendations or proposals are (is) compatible with individual uses shall be determined solely by each user and such user shall be solely responsible for any results, including but not limited to, any and all loss and damages incurred due to such uses. Users must implement and verify all testing and analyses for proving the safety and compatibility of final products that have been created or altered by using LOTTE Advanced Materials' materials or products. The data and values inserted and/or contained in this document may be changed due to quality improvement of the product without any prior notification.

※ The last update date : 07/23/2015

[CONVERT TO PDF](#)



To print the image properly, you need to set your print options on your Internet Explorer browser as follows.

[Menu > Tools > Internet Options] ▶ [Advanced > Printing > Check "Print background colors and images"]